

Tolerances for cold drawn bar							
Section	Size, di	ameter or	width acro	ss flats	Pern	nitted vari	ation
	mm				mm		
	>	6	<	18	+0	to	-0.070
Round	>	18	<	30	+0	to	-0.085
Hound	>	30	<	50	+0	to	-0.100
	>	50	≤	80	+0	to	-0.120
	>	80	<u> </u>	100	+0	to	-0.140
	≥	6 /	-5	18	+0	to	-0.090
	>	18/ /	<u>s</u>	30	+0	to	-0.110
Square and hexagon	>	30-	- s	50	+0	to	-0.130
nexagon	>	50	5//	80	+0	to	-0.160
	>	80	_ s/	105	+0	to	-0.250
	< 6	telam	et Ind	nstrie	C +0	to	-0.110
	>	18	≤	30	+0	to	-0.130
	>	30	≤	50	+0	to	-0.160
Flat (width)	>	50	<	80	+0	to	-0.190
riuc (widin)	>	80	<b>S</b>	100	+0	to	-0.220
	>	100	≤	130	+0	to	-0.350
	>	130	≤	160	+0	to	-1.000
	>	160	<b>S</b>	320	+1.0	to	-1.000
	<	18			+0	to	-0.110
	>	18	≤	30	+0	to	-0.130
Flat (thickness)	>	30	<	50	+0	to	-0.250
	>	50	≤	80	+0	to	-0.350

IS 9550: Tolerance and Dimension Requirements for Bright Steel Bars

Descripción

# IS 9550: Tolerance and Dimension Steels Requirements for Bright Steel Bars 1655

IS 9550:2001 specifies dimensional and straightness tolerances for cold drawn, turned, ground, and turned & reeled bright steel bars. These tolerances ensure precision, machinability, and compatibility in engineering applications.

At Steelmet Industries, we supply bright bars with full compliance to IS 9550, including tolerances for rounds, squares, flats, and hexagons across standard finish conditions.

# Permissible Finish Conditions Under IS 9550

The tolerances apply based on the type of finish. The following table maps finished conditions to the applicable tolerance classes as per IS 919 (Part 2):

Table 1: Tolerance Classes by Finish Condition

<b>Finished Condition</b>	<b>Applicable Tolerance Class</b>	Applicable Shapes
Drawn	h10, h11, h12	Round, Square, Hexagon
Turned	h10, h11	Round, Square, Hexagon
Turned & Reeled	h10, h11	Round, Square, Hexagon
Ground	h6 to h12	Round only

#### Standard Tolerances for Round Bars

Table 2: Tolerances on Nominal Dimensions (in mm)



Nominal Diameter (mm)	h6	h9	h10	h11
6 – 10	±0.009	?0.036	?0.058	?0.090
10 – 18	±0.011	?0.043	?0.070	?0.110
18 – 30	±0.013	?0.052	?0.084	?0.130
30 – 50	±0.016	?0.062	?0.100	?0.160

Note: All deviations are negative, i.e., undersize. For example, a 20 mm h9 bar will have actual size 19.948 to 20.000 mm.

#### Width and Thickness Tolerances for Flats

Drawn flats are also covered in IS 9550. Tolerances depend on width and thickness:

**Table 3: Width Tolerance (IS 919 h11)** 

Width (mn	n) Plus	(mm) Minus (mm)	YOU
Up to 18	0	0.11	16
18 – 30	0	0.13	Rais, steels
30 - 50	0	0.16	ight loss st
50 – 80	0	0.19	Bris

Table 4: Thickness Tolerance for Flats

# Thickness (mm) Max Negative Deviation (mm) e Cutting

6 – 10	0.09
10 – 18	0.11
18 = 30 2	0.13
30 – 50	0.16

# Straightness Tolerance

Unless otherwise agreed, the bar should not deviate more than **1.5 mm per 1 metre** of length.

## **Out-of-Shape Tolerance**

Deviations in non-round shapes (e.g., square, hexagon) shall not exceed half the specified tolerance for that dimension.

# **Edge Profile Requirement**

- Up to 150 mm width sharp corners without radius
- Above 150 mm slight undefined corner allowed (within 0.5 mm)



#### **Length Tolerances**

Standard length: 2.5 to 4.5 metres

• Short lengths (min 1.5 m): Up to 10% of the batch

• Specific lengths: Tolerance of +8 mm

#### Steelmet Industries — Your Source for Accurate Bright Bars

We produce dimensionally accurate bright bars conforming to IS:9550, ideal for CNC machining, threading, forging, and assembly line use.

Contact Steelmet Industries for full traceability and precision-tolerance bars.

## **FAQs on IS 9550 Tolerances and Dimensions**

What are h10 and h11 tolerances in IS 9550?

s Alloy ars, Steels h10 and h11 refer to dimensional tolerance classes defined in IS 919. h10 is tighter, while h11 allows slightly higher deviation. IS 9550 uses these classes based on finish condition and shape.

What is the straightness tolerance for bright bars?

IS 9550 permits up to 1.5 mm deviation in any 1 m length for straightness unless otherwise agreed between buyer and manufacturer.

Are tolerances in IS 9550 positive or negative?

Tolerances in IS 9550 are negatively disposed — meaning the bars are undersized from the nominal size.

By Steelmet Industries Team - Experts in Special Steels

#### Categoría

1. IS:9550-2001

#### **Etiquetas**

- 1. Bright Bar Tolerances
- 2. Dimensional accuracy
- 3. Flats and Squares
- 4. h10 h11 tolerances
- 5. IS 9550
- 6. Steelmet Industries
- 7. Turned Bars
- 8. drawn bars
- 9. ground bars

#### **Fecha**

18/07/2025



**Autor** admin

Steelmet Industries Bright Bars, Alloy
Steels, Free Cutting Steels, Stainless Steels