



16MnCr5 vs 20MnCr5 Steel: Key Differences in Composition, Heat Treatment, and Applications

Description

Introduction

16MnCr5 and 20MnCr5 are popular case-hardening steels used in high-stress components. While similar, their carbon and manganese differences impact:

- Core strength after heat treatment
- Case hardness depth
- Optimal applications

Steelmet Industries provides both grades as:

• Round bars (∅ 10mm – 300mm)

• Precision ground stock

• Custom-cut blanks

Chemical Composition Comparison

Element (%)	16MnCr5	20MnCr5
Carbon (C)	0.14 – 0.19	0.17 – 0.22
Manganese (Mn)	1.00 – 1.30	1.10 – 1.40
Chromium (Cr)	0.80 – 1.10	1.00 – 1.30
Phosphorus (P)	≤ 0.025	≤ 0.025

Element (%)	16MnCr5	20MnCr5
Sulfur (S)	≤ 0.035	≤ 0.035

Key Difference: 20MnCr5 has **higher carbon and chromium** for increased hardenability.

Mechanical Properties (After Case Hardening)

Property	16MnCr5	20MnCr5
Surface Hardness	58 ~ 62 HRC	58 ~ 62 HRC
Core Strength	800 ~ 1000 MPa	900 ~ 1100 MPa
Impact Toughness	Good	Moderate

20MnCr5 develops **10-15% higher core strength** but slightly lower toughness.

Key Differences & Applications

1. Heat Treatment Response

- **16MnCr5:** Better for **shallow case depths** (0.2-0.5mm)
- **20MnCr5:** Preferred for **deeper hardening** (1-2mm case depth)

2. Typical Uses

- **16MnCr5 Best For:**
 - Light-duty gears
 - Clutch components
 - Camshafts
- **20MnCr5 Best For:**
 - Heavy-duty transmission gears

- Axle shafts
- High-load bearings

3. Machinability

Both grades machine well in **annealed condition**, with 16MnCr5 being slightly easier.

Equivalents & Alternatives

Grade	DIN	AISI	ISO
16MnCr5	1.7131	5115	14MnCr5
20MnCr5	1.7147	5120	20MnCr5

For higher toughness: **18CrNiMo7-6**

Selection Guide

- **Moderate loads + better impact resistance** → 16MnCr5
- **Heavy loads + deeper hardening** → 20MnCr5

Steelmet Industries offers:

• Both grades in **annealed or pre-hardened** conditions

• Custom heat treatment services

• Precision machining stock

• **Request samples or datasheets** for your specific application.

Conclusion

While both are excellent case-hardening steels, **20MnCr5's higher carbon** makes it stronger for heavy-duty applications, while **16MnCr5** offers better toughness for dynamic loads.

Steelmet Industries stocks **16MnCr5 and 20MnCr5** in ready-to-machine forms → contact us for technical support and pricing.

Category

1. Posts

Tags

1. 16MnCr5
2. 20MnCr5
3. alloy steel comparison
4. carburizing steel
5. case hardening steel
6. engineering steel
7. gear steel
8. Steelmet Industries

Date

26/04/2026

Author

admin

Steelmet Industries - Bright Bars, Alloy Steels, Free Cutting Steels, Stainless Steels