



20MnCr5 Steel | Properties, Equivalents, Applications | Steelmet Industries

Description

20MnCr5 is a low-alloy case hardening steel known for its excellent wear resistance, core strength, and fatigue resistance. It is one of the most preferred grades for manufacturing components that need a tough core and hard, wear-resistant surface. At **Steelmet Industries**, we supply **20MnCr5 steel bars** in various forms including **hot rolled bars**, **bright bars**, and **custom profiles**, with complete traceability and consistent quality.

Chemical Composition of 20MnCr5 Steel

Element	Composition (%)
Carbon (C)	0.17 - 0.22
Manganese (Mn)	1.10 - 1.40
Chromium (Cr)	1.00 - 1.30
Silicon (Si)	0.10 - 0.40
Sulphur (S)	≤ 0.035
Phosphorus (P)	≤ 0.035

Mechanical Properties (Typical Values After Case Hardening)

Property	Value
Core Tensile Strength	750 - 1000 MPa
Case Hardness	58 - 62 HRC
Core Hardness	~30-35 HRC
Elongation	10 - 14%
Impact Resistance	Good (especially at the core)

Final properties depend on heat treatment and case depth.

• Equivalent Grades of 20MnCr5

Standard	Equivalent Grade
AISI / SAE	5120
DIN / EN	1.7147
IS (India)	20MnCr5 (IS 4432 / IS 5517)
JIS	SCM420H (similar)
BS	805A20 (similar)

• Applications of 20MnCr5 Steel

20MnCr5 is used in critical parts that require a hard, wear-resistant surface and a tough core:

- Gears and gear shafts
- Transmission components
- Camshafts and crankshafts
- Steering components
- Pins, bushings, and rollers
- Agricultural machinery parts
- Automotive and industrial equipment

It is ideal for **carburizing** and **case hardening applications** due to its structure and alloying elements.

• Machinability, Weldability & Heat Treatment

- **Machinability:** Good in normalized or annealed condition.

- **Weldability:** Moderate. Preheating and post-weld stress relieving recommended.

- **Heat Treatment:**

- Carburizing: 870-950°C
- Hardening: Oil quench at 780-820°C after carburizing
- Tempering: 150-200°C to reduce stresses without affecting case hardness

20MnCr5 is well-suited for **deep case hardening** applications with excellent wear resistance on the surface and toughness in the core.

20MnCr5 Steel Bars from Steelmet Industries

Steelmet Industries supplies 20MnCr5 steel bars in the following forms:

- **Bright Bars:** Drawn, Peeled, Ground
- **Hot Rolled Bars:** Rounds, Squares, Flats
- **Custom Profiles:** Round-corner squares, hex bars, D-shaped bars, and more
- **Available Sizes:**
 - Rounds: 12 mm to 90 mm
 - Custom shapes: As per customer drawings
- **Tolerances:** ISO H9, H10, H11 or customer-specified
- **Supply Condition:** As rolled, normalized, annealed, or case-hardened

Every bar is produced with **tight tolerances, smooth surface finish, and full traceability.**

Why Choose Steelmet Industries for 20MnCr5?

- Consistent quality from **VD route steel** (on request)
- Small batch or bulk availability
- Custom sizes, lengths, and shapes as per drawing
- Support for **OEMs, machinists, and exporters**
- **In-house QC** and **NABL-certified lab tie-ups**
- Competitive pricing and reliable delivery schedules

Certifications & Compliance

- Supplied with **Test Certificate (TC)** indicating heat number and analysis
- Complies with IS 4432, IS 5517, EN 10084, and customer-specific requirements
- Optional: Third-party inspections (TPI), UT reports, NABL-certified test reports

Enquire Now

Looking for high-quality 20MnCr5 steel bars with tight tolerances and full compliance?

Contact **Steelmet Industries** today or send your enquiry online.

Website: <https://www.steelmet.in>

© Use the contact form to get in touch with our sales and technical team.

Category

1. Posts

Tags

1. 20MnCr5 chemical composition

-
2. 20MnCr5 mechanical properties
 3. 20MnCr5 steel supplier
 4. 20MnCr5
 5. bright bars
 6. case hardening steel
 7. hot rolled steel
 8. Steelmet Industries

Date

05/05/2026

Author

admin

Steelmet Industries - Bright Bars, Alloy Steels, Free Cutting Steels, Stainless Steels